

IN THE CLAIMS

Please amend the claims as follows.

15. (Currently Amended) A process for fabricating a bump, wherein the bump is disposed on a chip that has an active surface and at least a bonding pad, and the bonding pad exposes the active surface, the process comprising:

forming a photoresist layer on the chip, having at least an opening that exposes the bonding pad;

performing an activation step, for depositing a medium layer directly on the bonding pad in the opening of the photoresist layer; and

performing an electroless plating process for forming a conductive layer within the opening of the photoresist layer to form at least a bump body directly in contact with ~~on~~ the medium layer; and

removing the photo resist layer.

16. (Original) The process of claim 15, wherein a material of the bump body is nickel.

17. (Original) The process of claim 15, wherein a material of the medium layer is zinc.

BEST AVAILABLE COPY

Claim 18 (canceled).

19. (Original) The process of claim 15, after forming the bump body, further comprising forming a bump body passivation layer on the bump body covering the bump body except for a portion of the bump body that connects to the medium layer.

Customer.No.: 31561
Application No.: 10/065,632
Docket No.: 8012-US-PA

20. (Original) The process of claim 19, wherein a material of the bump body
passivation layer is gold.

"BEST AVAILABLE COPY"